



PRODUCT DATA

Oil Base of America

12, 29 & 17 Series Oil Based Alkyd Coatings

Resin: Alkyd

Description: Oil Based fast dry synthetic alkyd enamel. Excellent color retention, flexible, good corrosion resistance, Apply direct to existing paint or over metal.

Colors: All colors available.

Viscosity: 65-80 Ku's.

VOC'S: less than 4.25 pounds per gallon.

Flashpoint: Above 65 F.

Thinner: Use S-971, S-974, or S-982. Consult representative for additional information.

Recommended Primer: 29 & 17 Series are primers to use under the 12 series topcoats.

Recommended Film Thickness: 1.5 mils to 2.5 mils DFT. (3.5 mils to 6 mils wft).

Coverage: 600 square feet per gallon @ 1 Mil. (Spray 175 square feet; roll 225 square feet is practical coverage).

Solids: 40% by volume.

Drying Times: @ 68 F To Touch 1 hour, recoat 4 hours, dry hard 4 hours. (Depending on humidity).

Products uses: An industrial maintenance coating primarily used in the marine industry. Use anywhere Enamel or oil based paints would be specified.

Surface Preparation: All surface areas should be clean and dry. Remove loose paint, rust, all dirt and oil prior to painting. The surface coated over will greatly determine the smoothness of the finish.

Application: Spray airless and conventional, roller, brush, mitt, dip.

The information, data, and suggestions contained herein are believed to be reliable, based on our knowledge and experience; however, it is expressly declared that the seller/ manufacturer does not guarantee the result to be obtained in the buyers processes. Seller/ Manufacturer expressly disclaims any implied warranty of merchantability or fitness for a particular purpose and /or any other warranty, express or implied. Buyer must make its own determination of the suitability of any product for its use. Nothing contained herein shall be construed to constitute inducement or recommendation to practice invention covered by any patent without the authority from the owner of the patent. (06/03)

[Return to Product Page](#)